

**DEPARTMENT OF TRANSPORTATION
STATE OF GEORGIA**

SUPPLEMENTAL SPECIFICATION

Section 832—Curing Agents

Delete Subsection 832.2.01.A and substitute the following:

832.2.01 Burlap or Cotton Fabric

A. Requirements

1. Use burlap or cotton fabric meeting these requirements:
 - Burlap that is 10 to 18 oz./yd² (340 to 610 g/m²) or two layers of 6 or 7 oz./yd² (200 or 235 g/m²)
 - Cotton fabric that is white, loosely woven, and not less than 7 oz./yd² (235 g/m²)
 - Strips of burlap or cotton fabric that are between 3 and 6 ft (0.9 and 1.8 m) wide and 3 ft (1 m) longer than the width of the slab to be covered
2. Use burlap and cotton fabrics that do not contain starch or other material that could stain the concrete. If the fabric is new, soak and dry it before use.

Delete Subsection 832.2.03.A and substitute the following:

832.2.03 Membrane Curing Compound

A. Requirements

1. Use membrane curing compounds listed in [QPL 16](#)
2. Use liquid membrane-forming compounds meeting AASHTO M 148 requirements.
3. Use membrane curing compounds evaluated by the National Transportation Product Evaluation Program (NTPEP) test facility or other approved test facility.

Office of Materials and Research